GC Application ID No.: **16123**



Silicone Caulk Extract on ZB-5HT

Zebron™ ZB-5HT, GC Cap. Column 15 m x 0.32 mm x 0.10 μm, Ea

Phase: 5% Phenyl 95% Dimethylpolysiloxane **Dimensions:** 15 meters x 0.32 mm x 0.1 μ m

Order No: 7EM-G015-02

Oven Profile: 60°C to 400°C at 25°C/min for 10min

Carrier Gas: Constant Flow Helium, 2.9 mL/min Injection: On-Column :1 0.1 µL @ 63°C **Detection:** Flame Ionization (FID) (425°C)


Analyst Note: Cured clear silicone caulk extracted with carbon disulfide.

16123



Products used in this application:





ANALYTES:

Silicone extract

©2025 Phenomenex Inc. All rights reserved.

For more information contact your Phenomenex Representative at support@phenomenex.com

