

GC Application

ID No.: 16126

Polywax[®] 850 on ZB-5HT

Column: Zebtron[™] ZB-5HT, GC Cap. Column 15 m x 0.32 mm x 0.10 µm, Ea

Phase: 5% Phenyl 95% Dimethylpolysiloxane

Dimensions: 15 meters x 0.32 mm x 0.1 µm

Order No: 7EM-G015-02

Oven Profile: 60°C to 400°C at 35°C/min for 8min

Carrier Gas: Constant Flow Helium, 2.9 mL/min

Injection: On-Column :1 0.1 µL @ 63°C

Detection: Flame Ionization (FID) (400°C)


Analyst Note: Sample was 0.65mg/mL in carbon disulfide. Polywax is a trademark of Petrolite Specialty Polymers Group.



Products used in this application:



16126



ANALYTES:

- 1 Polywax[®] 850

