

ASTM Method D5135-95: Analysis of Styrene on ZB-WAX

Column: Zebtron™ ZB-WAX, GC Cap. Column 30 m x 0.32 mm x 0.50 µm, Ea

Phase: Polyethylene Glycol (PEG)

Dimensions: 30 meters x 0.32 mm x 0.5 µm

Order No: 7HM-G007-17

Oven Profile: 80°C hold for 4min. to 150° at 30°C/min. hold for 6min.

Carrier Gas: Constant Flow Helium, 1.5 mL/min


Injection: Split 40:1 0.5 µL @ 170°C

Detection: Flame Ionization (FID) (240°C)

16142



Products used in this application:



ASTM Method D5135-95: Analysis of Styrene on ZB-WAX

ANALYTES:

- 1 Ethylbenzene
- 2 p-Xylene
- 3 m-Xylene
- 4 Isopropylbenzene
- 5 o-Xylene
- 6 Propylbenzene
- 7 p-Ethyltoluene
- 8 m-Ethyltoluene
- 9 Styrene
- 10 a-Methylstyrene
- 11 Phenylacetylene
- 12 beta-Methylstyrene
- 13 Benzaldehyde

