## **GC Application** ID No.: **19261**



## PolyWAX 1000 on ZB-1XT 5x0.53x0.15

Zebron™ ZB-1XT SimDist Metal, GC Cap. Column 5 m x 0.53 mm x 0.15 µm, Ea Column:

Phase: 100% Dimethylpolysiloxane **Dimensions:** 5 meters x 0.53 mm x 0.15  $\mu$ m

Order No: 7AK-G026-05

**Oven Profile:** 35 °C to 450 °C @ 15 °C/min for 10 min

**Carrier Gas:** Constant Flow Helium, 15 mL/min Injection: On-Column :1 1 µL @ 38°C **Detection:** Flame Ionization (FID) (450°C)


Analyst Note: Sample was 0.1% in CS2. Chromatogram is baseline subtracted.

19261



Products used in this application:





## **ANALYTES:**

1 PolyWAX 1000

©2025 Phenomenex Inc. All rights reserved.

For more information contact your Phenomenex Representative at support@phenomenex.com

